

ARKABS6130C

Color:White
Filling:Glass Fiber Reinforced、 High Rigidity、 Injection Molding

Basic Performance	Rated Value	Unit	Test Method
Density	1.26	g/cm	GB 1033
Fiberglass Content	25.4	%	GB 9345
Melt Flow Rate	4.5	g/10m	GB 3682
Mechanical	Rated Value	Unit	Test Method
Notched Izod Impact Strength	75.6	J/m	GB 1843
Tensile Strength	94.5	MPa	GB 1040
Flexural Strength	126	MPa	GB 9341
Fracture Elongation	3.4	%	GB 1040
Flexural Modulus	4250	MPa	GB 9341
Thermal	Rated Value	Unit	Test Method
Heat Distortion Temp(0.46MPa)	114	°C	GB 1634